APPLICATION

FOR

UNITED STATES LETTERS PATENT

APPLICANT NAME: Dalton et al.

TITLE: FINE-PITCH DEVICE LITHOGRAPHY USING A SACRIFICIAL HARDMASK

DOCKET NO.: FIS9-2001-0168

**INTERNATIONAL BUSINESS MACHINES CORPORATION
NEW ORCHARD ROAD, ARMONK, NY 10504**

FINE-PITCH DEVICE LITHOGRAPHY USING A SACRIFICIAL HARDMASK

RELATED APPLICATION

This application is related to U.S. Application No.
09/550,943 filed April 17, 2000, entitled "Protective hardmask
5   for producing interconnect structures," and assigned to the
same assignee as the present application. The disclosure of
the related application is incorporated herein by reference.

FIELD OF THE INVENTION

10   This invention relates to semiconductor processing, and
more particularly to critical dimension control in deep
submicron lithography for fabrication of interconnects in a
dual damascene process.

15

BACKGROUND OF THE INVENTION

Devices with multilevel interconnect structures have
become well known in the semiconductor industry. The dual
20   damascene process has proven to be a successful method for
building such structures. This process generally involves
embedding metal lines in an interlevel dielectric (ILD) layer,
and connecting metal layers by metallizing via holes formed in
the ILD. In order to improve the electrical performance of the
25   overall device, it is highly desirable that the ILD have a low
dielectric constant (k < 4). In addition, in very fine-pitch
(< 300 nm) devices, the lines and via holes must be etched into
the ILD with a critical dimension of about 100 nm. This

generally requires that the etch be performed with a hardmask. Furthermore, it is often desirable for part of the hardmask to remain on the ILD, to avoid a mask removal process which might damage the ILD; this layer is sometimes called a "residual hardmask" or "permanent hardmask." Accordingly, the hardmask layer in contact with the low-k ILD should also have a low dielectric constant.

A typical hardmask for formation of lines and vias in the ILD is shown schematically in Figure 1A. The ILD 10 is disposed on a barrier layer 1, which in turn covers the underlying level (not shown). The ILD is generally formed of a polymer such as an organic polyarylene ether thermoset dielectric, or a similar material. The hardmask includes three layers 11-13. Permanent hardmask layer 11 is formed of a low-k material (k < 4.5); examples of such materials are organosilicates such as SiCOH (containing Si, C, O and H); SiC; SiC:H; and amorphous Si containing C and H. Layer 11 is covered by layer 12, typically silicon nitride; thicknesses of layers 11 and 12 are approximately 500 Å and 350 Å respectively. Layer 13 is typically silicon dioxide with a thickness of approximately 1500 Å. The pattern for the metal lines is transferred to layer 13 ("line-level" lithography), resulting in formation of exposed areas 2 in the mask, as shown in Figure 1B. Further processing involves depositing a layer of resist 14 which is patterned to define via openings 4 ("via-level" lithography), as shown in Figure 1C. This requires that the resist 14 be at least partially planarized over the topography introduced by patterning layer 13. Layer 13 is also subject to faceting (that is, formation of facets 3), which leads to loss of critical-dimension control. The fidelity of the pattern transfer is also degraded by roughening of the line edge, caused by deposition thereon of plasma polymers.

Furthermore, as shown in Figure 1D, in subsequent processing the etched lines and via openings are overfilled

with metal 16 (often with a liner 15); the excess metal must then be removed, typically by chemical-mechanical polishing (CMP). If the metal 16 and liner material 15 are removed by CMP at nearly the same rate (for example, when metal 16 is copper and liner 15 is tungsten), the remaining hardmask must also function as a polish stop layer. The thin layer 12 of silicon nitride may not be effective as a CMP stop layer.

There is a need for an improved dual damascene process in which the hardmask structure permits processing with very high fidelity pattern transfer while retaining the advantages of low dielectric constant, and includes an effective CMP stopping layer.

SUMMARY OF THE INVENTION

The present invention addresses the above-described need by providing a dual damascene process using a hardmask structure including a sacrificial hardmask layer and which eliminates at least the oxide layer overlying the low-k dielectric layer.

In accordance with a first aspect of the invention, a method is provided in which three hardmask layers (lower, middle and top) are deposited on a low-k substrate. The top hardmask layer has a thickness less than about 200 Å. A first opening is formed in the top hardmask layer in accordance with a first pattern, thereby exposing a portion of the middle hardmask layer. A second opening is formed in that portion of the middle hardmask layer in accordance with a second pattern and a corresponding opening in the lower hardmask layer, thereby exposing a portion of the substrate. An opening is formed in the substrate, and metal is deposited therein. Excess metal may be deposited over the hardmask and then removed. Finally, the top hardmask layer is removed.

The material of the top hardmask layer may be a refractory

metal, a refractory metal nitride, a refractory metal alloy or
a conductive Si-based material such as doped Si or doped
amorphous Si, and is preferably a refractory metal nitride such
as TaN. The middle hardmask layer is preferably SiN. The

5   excess metal may be removed by CMP, with the top hardmask layer
having a lower polishing rate than the excess metal being
polished.

It should be noted that the process of forming the first
opening may include depositing a resist layer on the top

10   hardmask layer and subsequently removing the resist layer
therefrom; the middle hardmask layer protects the lower
hardmask layer from oxidation during removal of the resist
layer.

In accordance with a second aspect of the invention, a

15   method is provided in which a lower hardmask layer and a top
hardmask layer are deposited. A protective layer is formed in
a region of the lower hardmask layer adjacent to the top
surface thereof; this protective layer protects the lower
hardmask layer from oxidation when the resist removal is

20   performed. The protective layer may be formed by exposing the
lower hardmask layer to a plasma treatment which either forms a
protective nitride layer in the top surface region, or
densifies the lower hardmask layer in that region. The
protective layer has a thickness of approximately 100 Å.

25   In accordance with an additional aspect of the invention,
a method is provided in which a lower hardmask layer and a top
hardmask layer are deposited on the substrate. A first opening
is formed in the top hardmask layer in accordance with a first
pattern, thereby exposing a portion of the lower hardmask

30   layer. This process includes depositing a resist layer on the
top hardmask layer and subsequently removing the resist layer
therefrom; the resist layer is removed in a non-oxidizing
resist strip process, so that oxidation of the lower hardmask
layer is avoided. In particular, the resist may be removed in

a plasma resist strip process with a reducing chemistry.

It is noteworthy that the top hardmask layer is a thin sacrificial layer which can also serve as a CMP stopping layer, and that oxidation damage to the lower hardmask layer (which generally is of a low-k material) is avoided.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1A is a schematic illustration of a typical hardmask structure used in dual damascene processing.

Figures 1B-1D illustrate some of the processing difficulties encountered using the hardmask of Figure 1A.

Figures 2A-2H illustrate a dual damascene process using a three-layer hardmask in accordance with a first embodiment of the invention.

Figures 3A-3H illustrate a dual damascene process using a two-layer hardmask in accordance with a second embodiment of the invention.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

The hardmask structure of the present invention uses a thin (approximately 100-200 Å) sacrificial layer which overlies and protects the low-k dielectric hardmask layer, is an effective mask for etching the pattern of metal lines, and also provides an effective polishing stop in the metal CMP process.

First Embodiment: Three-layer hardmask

The structure of the hardmask of this embodiment is shown in Figure 2A. A thin hardmask layer 20 is used in place of the oxide layer 13 of the conventional hardmask (compare Figure 1A) and is the top layer of the three-layer hardmask structure. The underlying residual hardmask includes layer 11 and layer

12. The middle layer 12 is generally of a dielectric material having properties that are not degraded during typical processing steps (e.g. etching with a resist mask, resist strip, wet cleaning). This dielectric material may be SiO_2,

5   SiN, SiON, SiOF, or a similar material known in the art. The bottom layer 11 is generally of a low-dielectric-constant material such as SiC, SiC:H, an organosilicate (e.g. SiCOH), SiCNH, a spin-on silosesquioxane, carbon-doped oxide, organosilicate glass, silicon oxycarbide, amorphous

10   hydrogenated silicon carbide, amorphous hydrogenated silicon carbide/nitride, or a similar suitable material. It will be appreciated that this layer is subject to damage in various typical processing steps, and therefore requires a protective layer (in this case, dielectric layer 12). In particular, the

15   low-k layer 11 must be protected from oxidation during deposition of layer 20 and during resist strip processes (e.g. during resist rework).

      Layer 20 may be a metal, metal compound or alloy, semiconductor or dielectric, provided at least that (i) the

20   deposition of layer 20 does not damage the underlying layers, and in particular does not alter the desirable electrical properties of layers 10 and 11; and (ii) the polishing rate of layer 20 is low compared to that of the excess metal removed by CMP. Layer 20 is preferably a refractory metal (e.g. Ta, Ti,

25   W), a refractory metal nitride (e.g. TaN, TiN, WN), a refractory metal alloy (e.g. TaSiN, TiSiN, WSiN, TiW), a conductive Si-based material such as doped Si or doped amorphous Si, or some other metal (e.g. Cu, Al, Ag). More preferably, layer 20 is formed of a refractory metal nitride.

30   In particular, it has been found that a 150 Å layer of TaN provides good pattern fidelity while maintaining the desirable properties of layers 10 and 11.

      In this embodiment, the ILD layer 10 is formed of an organic polyarylene ether thermoset dielectric; the residual

hardmask layers 11 and 12 are SiC and SiN respectively; and
layer 20 is formed of TaN. Layers 11 and 12 may be formed by
chemical vapor deposition (CVD) or plasma enhanced CVD. Layer
11 may also be deposited in a spin-on process. Layer 20 may be

5   formed by physical vapor deposition or CVD.

Figures 2B-2H illustrate steps in a dual damascene process
using the hardmask of this embodiment. A resist layer 21 is
applied over the hardmask, and the pattern of metal lines is
developed therein. The line-level pattern is transferred to

10   the mask by etching openings 22 in layer 20, using Cl_2 or
Cl_2/BCl_3 chemistry (Figure 2B). The resist layer 21 is then
stripped and resist residues are removed, using methods known
in the art. Another resist layer 23 is then applied over the
mask, and the pattern of via openings 24 is developed therein

15   (Figure 2C). Compared to oxide layer 13, layer 20 is much less
subject to faceting and introduces much less topography
(compare Figures 1C and 2C).

The dual-damascene pattern is transferred first to the
residual hardmask, and then to the ILD, in a sequence of

20   etching steps. Layers 11 and 12 are etched using a
fluorocarbon-based chemistry. The ILD layer 10 is then
partially etched using a chemistry including one or more of O_2,
O_3, SO_2, SO_3, N_2, NH_3, N_2H_2, N_2H_4, H_2, CO_2, CO, CF_4, CHF_3, CH_2F_2 or
CH_3F; during this etch the resist layer 23 is also removed

25   (Figure 2D). An additional fluorocarbon-based etch is then
performed with layer 20 as a mask, opening layers 11 and 12 of
the hardmask in accordance with the metal line pattern
(openings 22). A further etching step, using chemistry similar
to that of the previous partial via etch, transfers the line-

30   level pattern into the ILD and completes the formation of the
vias (openings 24). As shown in Figure 2E, the metal line
pattern is transferred into the upper portion of the substrate
and the via pattern is transferred into the lower portion of
the substrate. This etching step stops at barrier layer 1,

which typically is formed of SiN or SiC. A fluorocarbon-based
etch then is used to open the barrier layer, so that
metallization of the via may contact the underlying level 100.
The width of the opening 24 at the bottom of the via may be as
5   small as approximately 100 nm.

     The metallization process preferably involves deposition
of a liner 25, followed by deposition of metal 26 in the vias,
in the metal line pattern, and over the hardmask (Figure 2F).
The excess metal is then polished away using a CMP process; the
10   portion of the liner 25 overlying the hardmask layer 20 is
generally also removed in the same CMP process. In particular,
if liner 25 is W while metal 26 is Cu, a standard CMP process
will not be selective between the two. It is necessary in such
a case for layer 20 to serve as a polishing stop (Figure 2G).
15   A typical CMP process for Cu will not be stopped by W but will
be stopped by Ti, Ta, TiN or TaN. Accordingly, a layer of TaN,
as described in this embodiment, provides an effective
polishing stop. Layer 20 is then removed in a separate
polishing process. At this point it is desirable to remove
20   layer 12 also, so that only the low-k layer 11 of the hardmask
structure remains (Figure 2H).

     The hardmask structure of this embodiment provides greatly
improved control of the critical dimension (metal line width
and spacing) compared to the hardmask structure of Figure 1A.
25   In addition, the hardmask of the present embodiment provides an
effective polishing stop, which in turn permits development of
a more reliable CMP metal removal process.

Second Embodiment: Two-layer hardmask
30   The structure of the hardmask of this embodiment is shown
in Figure 3A. Repeated reference numerals between Figures 2A-
2H and 3A-3H indicate corresponding structures. As in the
first embodiment, a thin sacrificial hardmask layer 20
comprises the top layer of the hardmask. The material of layer

20 may be a refractory metal (e.g. Ta, Ti, W), a refractory
metal nitride (e.g. TaN, TiN, WN), a refractory metal alloy
(e.g. TaSiN, TiSiN, WSiN, TiW), a conductive Si-based material
such as doped Si or doped amorphous Si, or some other metal

5   (e.g. Cu, Al, Ag). A preferred material is TaN, with a
thickness of about 150 Å. The underlying layer 31 is a low-k
dielectric such as SiCOH or a similar material as in layer 11
of the first embodiment, with a thickness of about 500 Å.

       In the present embodiment, the intermediate hardmask layer

10   (such as nitride layer 12) is eliminated; compare Figures 2A
and 3A. This is done by (i) treating the low-k layer 31 to
make it resistant to processing damage (e.g. damage by
oxidation during a resist strip process) and/or (ii) using a
resist strip process which does not oxidize the exposed surface

15   of layer 31.

       Layer 31 may be deposited on the ILD layer 10 using CVD or
plasma-enhanced CVD. In this embodiment, a 500 Å thickness of
SiCOH is deposited by plasma-enhanced CVD. The surface of
layer 31 is then exposed to a plasma (e.g. an NH_3 or nitride-

20   based plasma) which causes formation of a nitride in the top
surface region 31t of layer 31. Alternatively, the surface of
layer 31 may be exposed to a plasma treatment which densifies
the layer in surface region 31t, or layer 31 may be deposited
under conditions such that the material has increased density

25   in region 31t. The top surface region 31t has a thickness of
about 100 Å.

       In another alternative, the need for plasma treatment or
densification of the low-k layer 31 may be avoided by using
resist strip processes which do not oxidize the surface of

30   layer 31, as discussed in more detail below.

       The top hardmask layer 20 is then deposited on layer 31;
in this embodiment, a 150 Å thickness of TaN is deposited by
physical vapor deposition (PVD). As noted above, layer 20 may
be a metal, semiconductor or dielectric, provided that the

deposition process for layer 20 does not alter the properties of layer 31, and that the polishing rate of layer 20 is low compared to that of the metal used for the conducting lines.

Figures 3B-3H illustrate steps in a dual damascene process
5   using the two-layer hardmask of this embodiment. A resist layer 21 is applied over the hardmask; line-level patterning is then performed wherein hardmask layer 20 is patterned to produce openings 22 in accordance with the pattern of metal lines, using Cl_2 or Cl_2/BCl_3 chemistry (Figure 3B).

10   The resist layer 21 is then stripped using a non-oxidizing, reducing, or mildly oxidizing plasma process. This process is preferably a plasma process with a reducing chemistry; most preferably, an NH_3/H_2 or N_2/H_2 plasma process which prevents oxidation of the exposed surface of layer 31.
15   Alternatively, a selective solvent-based resist strip process may be used, such as an acetone-based acidic resist strip.

The via-level patterning is then performed, wherein resist layer 23 is applied and the pattern of via openings 24 is developed therein (Figure 3C). As in the first embodiment, the
20   line level pattern and via level pattern are transferred to the hardmask layer 31 and the ILD layer 10. The via pattern is etched into the SiCOH layer 31. A partial via etch is then performed, in which the via pattern is transferred into the ILD layer 10 (Figure 3D). The resist layer 23 is also removed
25   during this partial via etch step. An additional etch is then performed with layer 20 as a mask, opening layer 31 in accordance with the metal line pattern (thus creating openings 22 in the mask layer 31). A further etching step, using chemistry similar to that of the previous partial via etch,
30   transfers the line-level pattern into the upper portion of the ILD and completes the formation of the vias through the lower portion of the ILD (openings 24), as shown in Figure 3E.

The metallization process (preferably including deposition of liner 25 and metal 26) is then performed, resulting in the

structure shown in Figure 3F. The excess metal and exposed liner are then polished away using a CMP process, with layer 20 serving as a polishing stop layer as in the first embodiment. After the excess metal is polished (Figure 3G), layer 20 is removed in a separate polishing process to yield the structure shown in Figure 3H. It may be desirable to also remove the surface region 31t of layer 31 by CMP.

It is noteworthy that in this embodiment, the entire residual hardmask (consisting of layer 31) is a low-k material, along with the ILD layer 10.

The hardmask of the present embodiment offers all the advantages of the first embodiment, and in addition permits reduced process complexity and faster processing time, owing to the elimination of one layer from the conventional hardmask structure.

While the invention has been described in terms of specific embodiments, it is evident in view of the foregoing description that numerous alternatives, modifications and variations will be apparent to those skilled in the art. Accordingly, the invention is intended to encompass all such alternatives, modifications and variations which fall within the scope and spirit of the invention and the following claims.